

SUBSTRATE FOR REFLECTION TYPE LIQUID CRYSTAL DISPLAY
ELEMENT

BACKGROUND OF THE INVENTION

The present invention relates to a substrate for
10 reflection type liquid crystal display elements, and more
particularly to a substrate for a reflection type liquid
crystal display element that partially transmits light.

15 In recent years, with an object of making portable
electronic devices thinner and lighter, and also making
prolonged operation with a battery as a power source
possible, reflection type liquid crystal display elements
that make use of external light and are characterized by
20 having low power consumption have started to be used.
One such reflection type liquid crystal display element
that has been proposed is a semi-transmitting type liquid
crystal display element that uses a semi-transmitting
plate as a reflector plate, and can be used both as a
25 reflection type liquid crystal display element in bright
locations, and as a transmission type liquid crystal
display element using a backlight in dark locations (see
Japanese Laid-open Patent Publication (Kokai) No. 11-
002709).

30 The liquid crystal display element substrate used in
this semi-transmitting type liquid crystal display
element has a constitution in which a liquid crystal
layer is held between a pair of transparent substrates
provided with liquid crystal driving electrodes, and the
35 light scattering of the liquid crystal layer is

controlled by means of the magnitude of a voltage applied across the liquid crystal layer. Moreover, a plurality of semi-transmitting reflector plates each formed of a thin film of a metal such as aluminum are laminated on the back side substrate. The thin metal film is made sufficiently thin as to partially transmit light.

Moreover, recently a substrate for a reflection type liquid crystal display element having, in place of thin metal films forming the semi-transmitting reflector plates, a multilayer dielectric film comprised of a predetermined number of transparent films laminated on top of one another, with these transparent films being formed of two dielectric materials having different refractive indexes to one another, has been proposed by the assignee of the present application (see Japanese Patent Application No. 2000-204952, which is an application claiming priority based on Japanese Patent Application No. 11-32689).

However, according to the above-mentioned reflection type liquid crystal display element having a multilayer dielectric film, there is a possibility of ripples occurring in the optical reflection spectrum or optical transmission spectrum across the visible region, resulting in a problem in which it is not always possible to stably obtain an optical characteristic of a desired flatness, and coloring due to reflected light occurs.

Moreover, by making the number of layers in the multilayer dielectric film of the order of, for example, a few tens to a few hundreds, the degree of freedom to design the optical characteristic increases, with it being possible to set specifications such that the occurrence of ripples is suppressed, but there is a problem that as the number of layers is increased, the time taken to build up the layers increases to an industrially impractical extent.

SUMMARY OF THE INVENTION

It is an object of the present invention to provide a substrate for reflection type liquid crystal display elements having a multilayer dielectric film which can have fewer layers than according to the conventional art and can thus be formed in a shorter time, and which can stably obtain an optical characteristic of a desired flatness across the visible region, and moreover can prevent the occurrence of coloring due to reflection and transmission.

To attain the above object, the present invention provides a substrate for a reflection type liquid crystal display element, comprising a transparent substrate, and a reflective mirror formed on top of the transparent substrate, wherein the reflective mirror comprises a predetermined number of high-refractive-index first transparent films and low-refractive-index second transparent films laminated alternately on the transparent substrate, and wherein either or both of the first transparent films and the second transparent films are arranged such that a film thickness thereof increases progressively or decreases progressively with distance from the transparent substrate.

According to the above constitution, high-refractive-index transparent films and low-refractive-index transparent films are laminated alternately to form a multilayer dielectric film, and as a result the number of layers in the multilayer dielectric film can be made smaller, and hence the multilayer dielectric film can be made in a shorter time, the cost can be reduced, and mass production can be carried out more easily. Moreover, either or both of the high-refractive-index transparent films and the low-refractive-index transparent films are arranged such that the film thickness thereof increases

5

10

15

20

25

35

film having silicon dioxide as a principal component laminated on top of the transparent substrate. As a result, the adhesion between the transparent substrate and the transparent film closest to the transparent substrate is improved, impurities leaching out of the transparent substrate are intercepted, and hence an alkali passivation effect can be obtained.

More preferably, one of the first transparent films furthest from the transparent substrate is a photocatalytically active film having titanium dioxide as a principal component. As a result, dirt can be removed easily from the reflective mirror and hence the reflective mirror can be kept clean, and moreover adhesion to a color filter can be improved.

Preferably, the substrate for a reflection type liquid crystal display element further comprises a hydrophilic thin film having silicon dioxide as a principal component laminated on top of the one of the first transparent films. As a result, the hydrophobicity is mitigated and cleaning with an aqueous cleaning solution can be made effective.

More preferably, the substrate for a reflection type liquid crystal display element further comprises a transparent rugged scattering layer laminated between the transparent substrate and the base film. As a result, reflected light in the substrate is scattered to obtain a uniform intensity of reflection over a specific range of angle of visibility.

The above and other objects, features and advantages of the invention will become more apparent from the following detailed description taken in conjunction with the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1A shows a representative substrate for a reflection type liquid crystal display element;

FIG. 2 is a sectional view showing the schematic
10 structure of an example of a color liquid crystal display
element manufactured using the reflection type liquid
crystal display element substrate 1;

FIGS. 4A and 4B are graphs showing how the film thicknesses of the high-refractive-index transparent films 4 and the low-refractive-index transparent films 5 increase progressively with distance from the transparent substrate 2 in Examples shown in Table 1; specifically:

FIG. 4B shows the case for Example 13;

FIG. 5A shows the case for Example 6;

FIGS. 6A and 6B are graphs showing the film thicknesses of the high-refractive-index transparent films 4 and the low-refractive-index transparent films 5 of the Comparative Examples shown in Table 2;

35 specifically:

FIG. 6B shows the case for Comparative Example 2;

5 FIG. 8 is a graph showing an optical characteristic
for Example 6 shown in Table 1;

FIG. 10 is a graph showing an optical characteristic
10 for Example 14 shown in Table 1;

FIG. 12 is a graph showing an optical characteristic for Example 28 shown in Table 2;

FIG. 14 is a graph showing an optical characteristic for Comparative Example 2 shown in Table 2.

A description of embodiments of the present invention will now be given with reference to the drawings.

25 The present inventors conducted assiduous studies to
attain the above object, and as a result discovered that,
in a substrate for a reflection type liquid crystal
display element comprised of a reflective mirror formed
on top of a transparent substrate, wherein the reflective
30 mirror is comprised of a predetermined number of high-
refractive-index transparent films (first transparent
films) and low-refractive-index transparent films (second
transparent films) laminated alternately on the
transparent substrate, if either or both of the high-
35 refractive-index transparent films and the low-

refractive-index transparent films are arranged such that the film thickness thereof increases progressively or decreases progressively with distance from the transparent substrate, then the difference between the maximum light reflectance and the minimum light reflectance within the visible region (400 to 700nm) becomes small, and hence it becomes possible to stably obtain an optical characteristic of a desired flatness across the visible region, and to prevent the occurrence of coloring due to reflection and transmission.

The present invention was achieved based on the above findings.

A description will now be given of substrates for reflection type liquid crystal display elements according to embodiments of the present invention with reference to FIGS. 1A and 1B.

FIGS. 1A and 1B are sectional views showing the schematic structures of substrates for reflection type liquid crystal display elements according to embodiments of the present invention. FIG. 1A shows a representative example, whereas FIG. 1B shows an applied example thereof.

According to the reflection type liquid crystal display element substrate 1 in FIG. 1A, a predetermined number m (where m is a positive integer) of high-refractive-index transparent films 4 (first transparent films) formed of a high-refractive-index material that is a dielectric exhibiting low light absorption and low-refractive-index transparent films 5 (second transparent films) formed of a low-refractive-index material that is a dielectric exhibiting low light absorption are laminated alternately on a transparent substrate 2.

A silicate glass having a refractive index of about 1.50 to 1.55 at a wavelength of 550nm is generally used for the transparent substrate 2, with particular examples being a soda lime silicate glass, an alkali-free glass

05876179 "060701
702090" 679860

(for example NA35 glass made by NH Techno Glass Corp. or AN635 glass made by ASAHI GLASS CO., LTD.) or a low-alkali glass, but there is no such limitation and a transparent plastic or the like may also be used.

5 A multilayer dielectric film reflective mirror 6 is formed on the transparent substrate 2 by alternately laminating high-refractive-index transparent films 4 and low-refractive-index transparent films 5, with the total number of transparent films 4 and 5 being m. This
10 multilayer dielectric film reflective mirror 6 acts as a reflective film that reflects light. By appropriately setting the thicknesses of the high-refractive-index transparent films 4 and the low-refractive-index transparent films 5 and the predetermined number m, the
15 optical transmittance and the light reflectance can be set to desired values.

The transparent films 4 and 5 of the multilayer dielectric film reflective mirror 6 are arranged such that the film thicknesses thereof increase progressively with distance from the transparent substrate 2. Moreover,
20 as an alternative, it is also possible for the transparent films 4 and 5 to be arranged such that the film thicknesses thereof decrease progressively with distance from the transparent substrate 2, or for the
25 high-refractive-index transparent films 4 only to be arranged such that the film thickness thereof increases progressively with distance from the transparent substrate 2, or for the high-refractive-index transparent films 4 only to be arranged such that the film thickness thereof decreases progressively with distance from the
30 transparent substrate 2. By arranging the transparent films 4 and 5 in this way, the difference between the maximum and minimum values of the light reflectance and light transmittance across the visible region (400 to
35 700nm) becomes small, and it becomes possible to achieve

09876439 "060301

an optical characteristic of a desired flatness, and to prevent coloring due to reflection and transmission. In consideration of the effect of the multilayer dielectric film reflective mirror 6 in preventing coloring due to reflection and transmission, and also to reduce the time required for the building up of the layers and hence make mass production easier, it is preferable for the predetermined number m to be in the range of 3 to 14.

For the above reasons, the total number m of high-refractive-index transparent films 4 and low-refractive-index transparent films 5 laminated is preferably 3 to 14, but to make the light reflectance curve yet flatter and further improve the coloring prevention effect it is preferable for m to be at least 6, and to make mass production easier it is preferable for m to be not more than 12. Moreover, if it is important to further reduce the time required for the building up of the layers and hence make mass production yet easier, then m is preferably 3 or 4.

The above-mentioned optical transmittance and light reflectance are set in accordance with the required design specifications (which depend on the use etc.) of the substrate for a reflection type liquid crystal display element. For example, the light reflectance is set in the range of 5 to 95%; if the liquid crystal display element is to be used as a reflection type liquid crystal display element in a relatively bright environment, then the light reflectance is set to a high value (65 to 95%), whereas if the liquid crystal display element is to be used as a transmission type liquid crystal display element in a relatively dark environment, then the light reflectance is set to a low value (5 to 45%). If the light reflectance is set in the range of 45 to 65%, then a liquid crystal display element suitable for use both as a reflection type and a transmission type

The larger the difference in refractive index between the high-refractive-index transparent films 4 and the low-refractive-index transparent films 5 the better.

A dielectric material exhibiting low light absorption and having a refractive index of not more than 1.5 is preferable as the low-refractive-index material used in the low-refractive-index transparent films 5. Specifically, silicon dioxide (SiO_2) is used, but to reduce strain that is generated when the multilayer film is formed and improve chemical durability, it is also possible to use silicon dioxide as the principal component but also include small quantities of aluminum oxide or the like.

The high-refractive-index transparent film 4 furthest from the transparent substrate 2 is preferably a photocatalytically active film having titanium dioxide as the principal component; this high-refractive-index transparent film 4 acts as a photocatalytic film. Titanium dioxide generally exhibits a dirt-removing effect in which organic matter is decomposed (by oxidation) through the photocatalytic action of the titanium dioxide. As a result of the above, even if a

low-refractive-index transparent film 5 is laminated as the outermost layer of the multilayer dielectric film reflective mirror 6, during the manufacturing of the substrate for a reflection type liquid crystal display element, before a color filter 8 (see FIG. 2) is laminated on top of the multilayer dielectric film reflective mirror 6, irradiation with ultraviolet rays can be carried out, thus easily removing dirt from the multilayer dielectric film reflective mirror 6 and keeping the multilayer dielectric film reflective mirror 6 clean, and also improving adhesion to the color filter 8. Note that, in addition to the principal component titanium dioxide, materials such as iron, niobium and aluminum may also be included as secondary components.

Moreover, as shown in FIG. 1B, it is further preferable for a hydrophilic thin film 3 having silicon dioxide as the principal component to be laminated on top of the outermost layer of the multilayer dielectric film reflective mirror 6. Even if the The outermost high-refractive-index transparent film 4, as well as exhibiting a photocatalytic action as described above, also exhibits a property of repelling water (hydrophobicity), and hence if this high-refractive-index transparent film 4 is laminated as the outermost layer of the multilayer dielectric film reflective mirror 6, then there is a drawback in that when the surface of the multilayer dielectric film reflective mirror 6 is contaminated with organic substances in the air, cleaning with an aqueous cleaning solution becomes difficult. It is thus possible to mitigate this hydrophobicity by laminating the hydrophilic thin film 3 on top of the outermost high-refractive-index transparent film 4, thus ensuring that cleaning with an aqueous cleaning solution will be effective. To ensure that the photocatalytic action of the high-refractive-index transparent film 4

laminated immediately below the hydrophilic thin film 3 is not lost, the hydrophilic thin film 3 preferably has a thickness of not more than 10nm.

A base film 3a having silicon dioxide as the principal component may also be laminated on top of the transparent substrate 2, and in addition a transparent rugged scattering layer 15 composed principally of a thermosetting resin such as an acrylic resin, a polyimide resin, an epoxy resin or the like may also be laminated between the transparent substrate 2 and the base film 3a. The base film 3a improves the adhesion between the transparent substrate 2 or the transparent rugged scattering layer 15 and the innermost high-refractive-index transparent film 4, and also, in the case that soda lime silicate glass is used for the transparent substrate 2, prevents contamination from sodium ions leaching out of the transparent substrate 2. Moreover, if a transparent plastic substrate is used as the transparent substrate 2, then there is a possibility of water leaching out of the transparent substrate 2, in which case it is preferable for the base film 3a to be used laminated on top of a hard coating formed of a polyorganosiloxane.

The transparent rugged scattering layer 15 has minute irregularities formed on the surface thereof, and by means of these irregularities reflected light in the substrate is scattered to obtain a uniform intensity of reflection over a specific range of angle of visibility. The refractive index of the transparent rugged scattering layer 15 is preferably about the same as that of the transparent substrate 2.

FIG. 2 is a schematic sectional view showing the structure of an example of a color liquid crystal display element manufactured using the reflection type liquid crystal display element substrate 1 of FIG. 1B.

05876179 "060701

In FIG. 2, the color filter 8 comprised of red, green and blue cells arranged in a mosaic is laminated on top of the multilayer dielectric film reflective mirror 6. An overcoat 9 for protecting the color filter 8 is laminated on top of the color filter 8, and a transparent conductive film 10 formed of ITO or the like is laminated on top of the overcoat 9. A glass faceplate 12 is provided as the outermost layer furthest from the transparent substrate 2, and a transparent conductive film 10a formed of ITO or the like is laminated on the inside of the glass faceplate 12. A liquid crystal layer 11 is held between the transparent conductive film 10 and the transparent conductive film 10a. Moreover, a sealant 13 is provided around the periphery of the liquid crystal layer 11 so that the liquid crystals will not leak out. Note that, in the present embodiment, when investigating what values to use for the number of high-refractive-index transparent films 4 and low-refractive-index transparent films 5 in the multilayer dielectric film reflective mirror 6 and the film thicknesses thereof, in place of the laminate consisting of the color filter 8, the overcoat 9, the transparent conductive films 10 and 10a, the liquid crystal layer 11 and the sealant 13, a suppositious layer (matching layer 14) optically equivalent to this laminate was used. The refractive index of this matching layer 14 takes a value anywhere in the range of 1.50 to 1.55 depending on the types of the overcoat 9, the liquid crystal layer 11 and the like, but for the present embodiment the appropriate value was calculated to be 1.52.

Methods primarily used for forming the high-refractive-index transparent films 4 and the low-refractive-index transparent films 5 include a known vapor deposition method, a known ion plating method and a known sputtering method, but other methods may also be

used. When forming the high-refractive-index transparent films 4 and the low-refractive-index transparent films 5 using a vapor deposition method, quartz glass pellets, a titanium dioxide sintered body and a zirconium dioxide sintered body are used as the deposition materials, and the vapor deposition is carried out while feeding in a moderate amount of oxygen from the outside. When a sputtering method is used, radio frequency sputtering is carried out with quartz glass as the target, or titanium metal is reacted with oxygen and sputtering is carried out.

FIG. 3 is a schematic view showing the structure of an example of a manufacturing device for manufacturing the reflection type liquid crystal display element substrate of FIG. 1B.

The manufacturing device shown in FIG. 3 is a cylindrical type sputtering film-forming device. A titanium metal target 303 is stuck onto one cathode 302, and a quartz glass target 304 is stuck onto another cathode 302. A plurality of glass substrates 305, which are transparent substrates 2 as described above, are stuck onto the peripheral surface of a cylindrical substrate holder 301 having a rotating shaft. By rotating the substrate holder 301, a multilayer dielectric film reflective mirror 6 is deposited onto each glass substrate 305. Specifically, when a glass substrate 305 passes in front of the surface of the titanium metal target 303, a titanium dioxide film is formed as a high-refractive-index transparent film 4, and when the glass substrate 305 passes in front of the surface of the quartz glass target 304, a silicon dioxide film is deposited as either a low-refractive-index transparent film 5 or the hydrophilic thin film 3. By applying electrical power to the titanium metal target 303 and the quartz glass target 304 alternately, titanium

05876179 "050701"

using the manufacturing device described above under the film deposition conditions described above, that is a 50vol%-oxygen 50vol%-argon atmosphere at a total pressure of 0.4Pa for the titanium dioxide (TiO_2) films and an argon atmosphere at a total pressure of 0.4Pa for the silicon dioxide (SiO_2) films, and with the number of layers deposited and the thicknesses thereof being as shown in Tables 1 and 2. In this way, samples shown in Tables 1 and 2 (Examples 1 to 30 and Comparative Examples 1 and 2) were prepared.

Note that, in the present embodiment, the samples shown in Tables 1 and 2 were suppositious optical multilayered bodies formed using a matching layer 14 (refractive index 1.52) in place of the laminate consisting of a color filter 8, an overcoat 9, transparent conductive films 10 and 10a, a liquid crystal layer 11 and a sealant 13 that should be laminated on top of the multilayer dielectric film reflective mirror 6, wherein the matching layer 14 was optically equivalent to this laminate, and then a glass faceplate 12 (refractive index 1.50) laminated on top of the matching layer 14. The suppositious optical multilayered bodies formed in this way were approximately equivalent to the corresponding actual reflection type liquid crystal display elements.

09876179-050701

Table 1

		NO. OF LAYERS	FILM MATERIAL/THICKNESS (UNIT:nm)														HYDROPHILIC FILM		
			BASE FILM	LAYER 1	LAYER 2	LAYER 3	LAYER 4	LAYER 5	LAYER 6	LAYER 7	LAYER 8	LAYER 9	LAYER 10	LAYER 11	LAYER 12	LAYER 13			LAYER 14
			SiO ₂	TiO ₂	SiO ₂	TiO ₂	SiO ₂	TiO ₂	SiO ₂	TiO ₂	SiO ₂	TiO ₂	SiO ₂	TiO ₂	SiO ₂	TiO ₂			SiO ₂
EXAMPLE	1	5		16.4	34.5	61.4	37.1	81.0											
	2			80.5	38.7	58.7	29.5	22.3	21.1										
	3			11.4	64.1	23.7	116.7	63.7	159.2										
	4			61.0	115.0	25.3	50.4	16.4	6.3										
	5			16.3	39.5	53.9	93.4	64.2	141.1										
	6			60.0	87.8	55.4	26.6	20.2	20.0										
	7			42.3	41.4	53.8	69.6	60.5	105.0	70.1	117.4	80.8	159.1						
	8			77.9	97.3	71.3	74.8	63.2	62.9	43.3	41.4	39.8	21.0						
	9			39.9	53.8	51.9	56.7	69.9	57.1	84.2	81.0	85.6	87.0	91.5	89.9				
	10			89.3	121.8	85.0	90.6	83.9	84.6	64.8	55.6	64.1	52.8	48.3	36.6				
	11			41.1	63.0	48.9	73.7	55.2	77.6	66.5	101.9	72.1	108.0	77.9	117.1	88.3	132.4		
	12			87.4	124.7	73.2	115.3	68.8	104.7	62.8	92.7	47.1	80.9	44.9	69.8	39.2	37.1		
	13			38.3	38.8	58.3	65.7	60.1	95.9	72.3	113.4	82.1							
	14			77.1	99.2	69.0	83.9	60.9	56.4	47.1	39.3	39.4							
	15			38.9	34.7	40.7	88.2	50.1	94.2	57.9	106.7	75.5							
	16			79.7	105.6	59.2	95.2	50.3	87.6	41.2	38.5	37.0							
	17		6	80.5	38.7	58.7	29.5	22.3	21.1										
	18		10	42.3	41.4	53.8	69.6	60.5	105.0	70.1	117.4	80.8	159.1						
	19			38.3	38.8	58.3	65.7	60.1	95.9	72.3	113.4	82.1							3.0
	20		9	38.3	38.8	58.3	65.7	60.1	95.9	72.3	113.4	82.1							8.0

<SUBSTRATE SIDE> <-

-> <OUTSIDE>

<SUBSTRATE SIDE> ←

→ <OUTSIDE>

Table 2

		NO. OF LAYERS	FILM MATERIAL/THICKNESS (UNIT:nm)														HYDROPHILIC	
			BASE FILM	LAYER 1	LAYER 2	LAYER 3	LAYER 4	LAYER 5	LAYER 6	LAYER 7	LAYER 8	LAYER 9	LAYER 10	LAYER 11	LAYER 12	LAYER 13	LAYER 14	FILM
				SiO ₂	TiO ₂	SiO ₂	TiO ₂	SiO ₂	TiO ₂	SiO ₂	TiO ₂	SiO ₂	TiO ₂	SiO ₂	TiO ₂	SiO ₂	TiO ₂	SiO ₂
EXAMPLE	21	10		34.9	47.8	39.1	79.1	49.9	100.2	69.5	89.8	84.0	31.6					
	22			86.0	89.9	72.9	85.0	50.1	100.1	40.0	42.3	34.9	65.1					
	23	12		33.6	66.5	48.4	53.8	71.4	60.3	80.9	73.4	84.1	99.9	88.0	99.5			
	24			90.9	123.5	85.1	95.6	82.7	100.0	66.9	50.2	59.7	71.9	42.3	92.8			
	25	14		36.0	71.5	50.0	73.7	53.1	74.5	66.3	111.0	71.0	104.0	78.1	117.9	87.4	141.6	
	26			87.2	123.9	77.1	104.6	70.0	112.5	64.9	83.9	46.6	86.1	44.0	76.3	36.0	36.3	
	27	3	10.0	10.1	64.4	75.8												
	28		10.0	68.9	42.1	10.2												
	29	1	10.0	10.1	48.6	72.5	93.1											
	30		10.0	66.9	44.0	10.3	38.2											
COMPARATIVE EXAMPLE	1	6		58.7	29.5	22.3	21.1	80.5	38.7									
	2	8		50.1	94.2	57.9	106.7	75.5	34.7	38.9	88.2	40.7						

→<OUTSIDE>

<SUBSTRATE SIDE> ←

<SUBSTRATE SIDE> ←

→<OUTSIDE>

In Tables 1 and 2, 'No. of layers m' indicates the total number of high-refractive-index transparent films 4 and low-refractive-index transparent films 5, and 'film material/thickness (nm)' shows the order in which the films were deposited, and the material and thickness of each film.

In Examples 1, 3, 5, 7, 9, 11, 13, 15, 18, 19, 20 and 29 shown in Tables 1 and 2, the high-refractive-index transparent films 4 and the low-refractive-index transparent films 5 were both arranged such that the film thicknesses thereof increase progressively with distance from the transparent substrate 2. In particular, the way in which these film thicknesses change is shown in FIG. 4A for Example 5 and FIG. 4B for Example 13. On the other hand, in Examples 2, 4, 6, 8, 10, 12, 14, 16, 17 and 30 shown in Tables 1 and 2, the high-refractive-index transparent films 4 and the low-refractive-index transparent films 5 were both arranged such that the film thicknesses thereof decrease progressively with distance from the transparent substrate 2. In particular, the way in which these film thicknesses change is shown in FIG. 5A for Example 6 and FIG. 5B for Example 14.

Moreover, in Examples 21, 23, 25 and 27, the high-refractive-index transparent films 4 only were arranged such that the film thickness thereof increases progressively with distance from the transparent substrate 2, and conversely, in Examples 22, 24, 26 and 28, the high-refractive-index transparent films 4 only were arranged such that the film thickness thereof decreases progressively with distance from the transparent substrate 2.

In Comparative Examples 1 and 2 in Table 2, the high-refractive-index transparent films 4 and low-refractive-index transparent films 5 were built up without controlling the film thicknesses thereof in any

090701 060701 060701

In Examples 17 and 18, a base film 3a having SiO₂ as the principal component was deposited between the

For each of the above samples, visible light was irradiated from one surface, and the optical transmittance (%) and the light reflectance (%) were measured for this visible light at wavelengths corresponding to the red, green and blue components. The measurement results are shown in Tables 3 and 4.

For each of the above samples, visible light was irradiated from one surface, and the optical transmittance (%) and the light reflectance (%) were measured for this visible light at wavelengths corresponding to the red, green and blue components. The measurement results are shown in Tables 3 and 4.

Table 3

		NO. OF LAYERS (m)	OPTICAL REFLECTANCE (%)				OPTICAL TRANSMITTANCE (%)			
			R (640nm)	G (530nm)	B (460nm)	ΔR	R (640nm)	G (530nm)	B (460nm)	ΔT
EXAMPLE	1	5	31.3	28.8	32.9	4.1	66.7	70.4	66.1	4.3
	2	6	30.6	28.7	31.3	2.6	67.4	70.5	67.7	3.1
	3		37.8	36.8	39.5	2.7	60.4	62.4	58.3	4.1
	4		38.6	37.5	40.1	2.6	59.8	61.6	57.5	4.1
	5		46.7	46.1	47.6	1.5	51.4	53.0	50.0	3.0
	6		46.1	45.9	46.9	1.0	51.9	53.1	50.2	2.9
	7	10	75.0	75.9	75.4	0.9	25.6	25.7	21.3	4.4
	8		76.2	76.6	74.1	2.5	21.8	22.6	24.9	3.1
	9	12	75.4	75.2	76.5	1.3	22.6	23.9	24.3	1.7
	10		72.3	73.3	71.2	2.1	25.7	25.8	27.4	1.7
	11	14	84.8	82.3	83.6	2.5	13.8	16.9	15.8	3.1
	12	9	84.6	82.7	84.7	2.0	12.7	16.1	14.6	3.4
	13		73.7	74.1	77.8	4.1	24.3	25.1	21.2	3.9
	14		76.3	76.7	73.8	2.9	21.8	22.6	25.2	3.4
	15		79.2	79.3	78.3	0.9	18.9	20.0	20.8	1.9
	16		78.4	79.5	80.1	1.7	19.7	19.8	19.0	0.8
	17	6	28.9	26.7	30.5	3.8	69.2	72.5	68.7	3.8
	18	10	73.9	72.3	76.1	3.8	24.1	26.9	22.9	4.0
	19	9	73.8	74.2	77.9	4.1	24.3	25.0	21.2	3.8
	20		73.8	74.2	78.0	3.9	24.2	25.0	21.2	3.9

T02090"62T92860

Table 4

		NO. OF LAYERS (m)	OPTICAL REFLECTANCE (%)				OPTICAL TRANSMITTANCE (%)			
			R	G	B	ΔR	R	G	B	ΔT
			(640nm)	(530nm)	(460nm)		(640nm)	(530nm)	(460nm)	
EXAMPLE	21	10	74.0	74.3	72.3	2.0	24.3	24.9	26.4	2.1
	22		75.3	75.4	75.2	0.2	23.7	24.0	23.0	1.0
	23	12	73.9	76.9	77.2	3.3	24.2	22.2	20.7	3.5
	24		72.1	75.9	75.7	3.8	25.9	23.2	23.0	3.5
	25	14	84.8	82.3	83.6	2.5	15.0	17.0	15.3	2.0
	26		82.5	81.8	80.3	2.2	15.5	16.5	15.3	1.2
	27	3	16.9	20.1	22.6	5.7	81.1	79.1	76.3	4.8
	28		18.3	19.1	20.2	1.9	79.7	80.0	78.6	1.4
	29	4	18.1	18.2	21.0	2.9	80.0	81.0	79.9	1.1
	30		19.0	19.3	19.8	0.8	79.0	79.9	79.0	0.9
COMPARATIVE EXAMPLE	1	6	41.4	15.9	45.0	29.1	56.7	83.3	54.0	29.7
	2	8	50.0	93.0	68.3	43.0	48.1	6.2	30.7	41.9

In Tables 3 and 4, the optical transmittance (%) indicates the percentage of the visible light that was transmitted through the sample at wavelengths corresponding to the red (R) component (640nm), the green (G) component (530nm) and the blue (B) component (460nm); the light reflectance (%) indicates the percentage of the visible light that was reflected by the sample at the wavelengths corresponding to the red, green and blue components. ΔR and ΔT indicate the difference between the maximum and minimum values (i.e. the size of the ripples) for the light reflectance and the optical transmittance respectively.

It can be seen from Tables 3 and 4 that by setting the number of high-refractive-index transparent films 4

and low-refractive-index transparent films 5 laminated and the thicknesses thereof as in Tables 1 and 2, for each of Examples 1 to 30 the difference between the maximum and minimum values of the light reflectance is not more than about 10% at the wavelengths corresponding to each of the red, green and blue components of the visible light.

A description of an optical characteristic of the substrate for a reflection type liquid crystal display element of Examples and Comparative Examples of the present invention will now be given with reference to FIGS. 7 to 14.

FIG. 7 is a graph showing the optical characteristic for Example 5 shown in Table 1. Similarly, FIGS. 8, 9 and 10 are graphs showing the optical characteristic for Examples 6, 13 and 14 respectively shown in Table 1.

FIG. 11 is a graph showing the optical characteristic for Example 27 shown in Table 2. Similarly, FIGS. 12, 13 and 14 are graphs showing the optical characteristic for Example 28, Comparative Example 1 and Comparative Example 2 respectively shown in Table 2. As the optical characteristic shown in FIGS. 7 to 14, the light reflectance (%) for an angle of incidence of 0° is shown plotted along the ordinate against wavelength (nm) along the abscissa.

As shown in FIGS. 7 to 12, the optical characteristic for each of Examples 5, 6, 13, 14, 27 and 28 is approximately flat, with no significant ripples occurring within the visible region. Conversely, the optical characteristics of Comparative Example 1 (FIG. 13) and Comparative Example 2 (FIG. 14) are not flat, with ripples occurring within the visible region in both cases.

Moving on, measurements were taken with regard to the degree of photocatalytic activity, the hydrophilicity

0906179-060701
10/2090 "6/79/850

5 Table 5

10
15
20

Triolein was applied onto the surface of the outermost layer of the multilayer dielectric film reflective mirror 6 of each of the above samples with the matching layer 14 and the glass faceplate 12 removed, and irradiation was carried out with ultraviolet rays at an intensity of 3mW/cm^2 for 24 hours using a black light. 'Residual triolein' in Table 5 indicates the percentage of the triolein remaining on the surface of the aforementioned outermost layer after the irradiation. The lower this figure, the better the cleaning effect of removing dirt and the like. 'Contact angle' in Table 5 is the contact angle when a drop of water was dropped onto the surface of the outermost layer of the multilayer dielectric film reflective mirror 6 after this surface had been irradiated with ultraviolet rays at an intensity of 3mW/cm^2 for 30 minutes using a black light. The lower

this figure, the higher the hydrophilicity.

Regarding the adhesion to the color filter, a color filter 8 was formed on top of the multilayer dielectric film reflective mirror 6 of each of the above samples, and then the adhesion at the interface between the multilayer dielectric film reflective mirror 6 and the color filter 8 was evaluated using a tape test. There were 4 evaluation levels; specifically, '◎' indicates no peeling off whatsoever, '○' indicates that 0 to 1% of the total area peeled off, '△' indicates that 1 to 3% of the total area peeled off, and 'X' indicates that more than 3% of the total area peeled off.

As shown in Table 5, with each of Examples 1 and 13 to 16, for which a photocatalytically active TiO_2 film was laminated as the outermost layer, compared with Comparative Example 1, the residual triolein percentage was lower, and good adhesion to the color filter 8 was obtained. Moreover, with Examples 19 and 20, for which an SiO_2 film of thickness not more than 10nm, that is a hydrophilic thin film, was laminated on top of the photocatalytically active TiO_2 film, compared with Comparative Example 1, once again the residual triolein percentage and the contact angle were lower, and good adhesion to the color filter 8 was obtained.

05076479.060704
T04090"6792850